

**2013 APPS - KL**

# **The Importance of Charge Testing in Delivering Well Performance**

**APPS-13-12**

*Presented by*

Mark S Brinsden

Shell

Chair API SC19B




AMERICAN PETROLEUM INSTITUTE

Mark Brinsden  
API SC 19B

# 1. Contents

1. Contents
2. Review of API testing for charge performance
3. Using API testing
4. Selecting Charges and Guns for well performance
5. Modelling for Performance
6. Conclusions and Way Forward



## 2. Review of API testing for charge performance


API RP19B is currently being rewritten  
to bring it up to date.

One of the key drivers, is about making it clear  
that you need to use the right kind of testing  
to really understand how your gun and  
charge are going to behave in your  
reservoir.


## 2. Review of API testing for charge performance

### Section 1: Evaluation under surface conditions in concrete targets

- Provides a fit-for-purpose method of identifying – variability in charge data (LP & EHD) – charge interference – verified QC test – but also used as benchmark for charge penetration.
- Although designed to be consistent and arguably an improvement on API RP 43 Section 1 target – is know to be inconsistent and unsuitable reference for reservoir penetration benchmark.
- A new data sheet has been drafted including disclaimer...





***“Penetration Data recorded in API RP19B Section 1 may not directly correlate to penetration downhole”.***



## 2. Review of API testing for charge performance

### Section 2: Evaluation under stress conditions in rock targets


- Basic test to measure stressed rock penetration profile and performance.
- Can be expanded to different rocks, diameters and stress conditions.
- *Could also be used as one of the standards for improved charge performance testing using a selection of outcrop rock or synthetic rock targets.*



## 2. Review of API testing for charge performance

### Section 4: Evaluation of flow performance under simulated downhole conditions

- Suitable for evaluating flow, penetration and dynamic perforating event under simulated wellbore and reservoir conditions.
- *Section 4 has been rewritten due to need to improve the correlation in performance between the different test cells in the market and has been submitted to vote, has passed for issuing.*




## 2. Review of API testing for charge performance

Section 3: Temperature Performance

Section 5: Debris Evaluation

Section 6: Gun Swell – (New)

All three of these also have a great deal of relevance in understanding how well charges and guns perform under reservoir conditions.



# 3. Using API testing – Charge consistency



## REGISTERED DATA SHEET PERFORATING SYSTEM EVALUATION, API RP 19B SECTION 1



Service Company Schlumberger Explosive weight 27.0 gm, HMX Powder, Case Material Steel  
 Gun OD & Trade Name 3.50-in. High Shot Density Max Temp, °F 400 1 hr 3 hr 24 hr 300 100 hr 200 hr  
 Charge Name PowerJet Omega 3506, HMX Maximum Pressure Rating 25,000 psi, Carrier Material Steel  
 Manufacturer Charge Part No. 100019953 Date of Manufacture 06/28/04 Shot Density Tested 6 Shots/ft  
 Gun Type TCP and Wireline Hollow Carrier, Non Reusable Recommended Minimum ID for Running See Remarks in.  
 Phasing Tested 72 degrees, Firing Order: X Top down X Bottom up Available Firing Mode: X Selective X Simultaneous  
 Debris Description Small steel chips Debris Weight n/a gm/charge, Debris n/a in<sup>3</sup>/charge  
 Remarks Maximum gun diameter after shooting in liquid is 3.72 in.

### SECTION 1 - CONCRETE TARGET

Casing Data 5 OD, Weight 15.0 lb/ft, API Grade, L-80 Date of Section 1 Test 08/18/04  
 Target Data 120 OD, Amount of Cement 15,600 lb, Amount of Sand 31,200 lb, Amount of Water 8,105 lb.  
 Date of Compressive Strength Test 08/18/04 Briquette Compressive Strength 6,155 psi, Age of Target 28 days

Shot No.	No 1	No 2	No 3	No 4	No 5	No 6	No 7	No 8	No 9	No 10	No 11
Clearance, in.	0.27	0.81	0.81	0.27	0.00	0.27	0.81	0.81	0.27	0.00	0.27
Casing Hole Diameter, Short Axis, in	0.45	0.32	0.39	0.36	0.51	0.47	0.38	0.41	0.48	0.49	0.47
Casing Hole Diameter, Long Axis, in	0.46	0.32	0.42	0.37	0.53	0.48	0.41	0.43	0.50	0.52	0.47
Average Casing Hole Diameter, in.	0.46	0.32	0.41	0.37	0.52	0.48	0.40	0.42	0.49	0.51	0.47
Total Depth, in.	46.8	45.6	40.1	45.7	48.9	33.7	52.8	44.5	42.1	48.6	50.7
Burr Height, in.	0.08	0.01	0.03	0.05	0.12	0.03	0.03	0.05	0.06	0.13	0.01

Shot No.	No 12	No 13	No 14	No 15	No 16	No 17	No 18	No 19	No 20	No 21	No 22	Average
Clearance, in.	0.81	0.81	0.27	0.00								xxxx
Casing Hole Diameter, Short Axis, in	0.32	0.36	0.49	0.51								0.43
Casing Hole Diameter, Long Axis, in	0.32	0.37	0.51	0.51								0.44
Average Casing Hole Diameter, in.	0.32	0.37	0.56	0.51								0.44
Total Depth, in.	48.1	45.0	24.6	44.5								44.2
Burr Height, in.	0.01	0.02	0.09	0.14								0.06

Remarks \_\_\_\_\_

### WITNESSING INFORMATION

Date of Notice of Intent to Test: 07/19/04 Witnessed by: Truda Stevens - Quality Systems Management  
 Other Activities Witnessed: Target Pouring \_\_\_\_\_ Briquette: Preparation \_\_\_\_\_ Testing \_\_\_\_\_ Burr Height Measurements \_\_\_\_\_ Samples Taken: Concrete X Casing X


### CERTIFICATION

I certify that these tests were made according to the procedures as outlined in API RP 19B: Recommended Practices for Evaluation of Well Perforators, First Edition, November 2000. All of the equipment used in these tests, such as the guns, jet charges, detonator cord, etc., was standard equipment with our company for the use in the gun being tested and was not changed in any manner for the test. Furthermore, the equipment was chosen at random from stock and therefore will be substantially the same as the equipment, which would be furnished to perforate a well for any operator. The American Petroleum Institute neither endorses these test results nor recommends the use of the perforator system described.

x CERTIFIED BY [Signature] Perforating Prod. Dev. Mgr. Oct 12, 2004 Schlumberger 14910 Airline Road Rosharon, TX 77583  
 RECERTIFIED \_\_\_\_\_ (Company Official) \_\_\_\_\_ (Title) \_\_\_\_\_ (Date) \_\_\_\_\_ (Company) \_\_\_\_\_ (Address)




### 3. Using API testing



- Unstressed Section 1 concrete data provides no strong correlation to stressed rock penetration or in-situ reservoir rock penetration – this has been known for years.

### 3. Using API testing



### 3. Using API testing

So we understand from this that :-

1. There is no general correlation between surface concrete penetration and down hole
2. We need to select charges for specific reservoir type
3. Relying on concrete penetration is only suitable for very simple operations
4. A charge can be great for certain reservoir conditions but relatively less useful for others

## 4. Selecting Charges and Guns for well performance

What are the kind of things we need to think about when selecting a gun and charge for a reservoir :-

1. How is gun to casing clearance going to effect performance.

Testing the charge under simulated downhole conditions gives us actual penetration and casing hole diameter.

Actual Example:-

2-7/8in Premium Gun penetrating 9-5/8in casing into 6000psi UCS Stressed Target

Gun Clearance	Target Penetration	Casing Entrance Hole
0.5	10.3	0.25
5.0	3.9	0.15

## 4. Selecting Charges and Guns for well performance

What are the kind of things we need to think about when selecting a gun and charge for a reservoir :-

2. How is penetrating double casing going to effect performance.

Actual Example:-

2-7/8in Premium Gun penetrating 5-1/2in casing cemented in 9-5/8in casing into 6000psi UCS Stressed Target

Gun Clearance	Target Penetration	Casing 1 Entrance Hole	Casing 2 Entrance Hole
0.5	10.3	0.25	NA
0.5	7.1	0.25	0.15


## 4. Selecting Charges and Guns for well performance

What are the kind of things we need to think about when selecting a gun and charge for a reservoir :-

3. Is there poor Vert. Perm., is the reservoir interbedded with impermeable Layers. Look at relative performance of higher shot density guns – lower penetration, but access every layer.
4. Reservoir temperature – is the gun suitable for your operating temperature, can you safely use an HNS charge at borderline temperatures. Use temp charts – but what about the change in charge performance with temperature – use section 3.
5. Is gun debris an issue and if so is the data in Sect 5 suitable for you to work out if a gun is suitable?
6. Will the gun operate in your downhole conditions, is gas flowing past your gun, is the gun capable of being shot in gas. Will the gun swell be an issue – we want the largest gun probably for clearance and penetration – but will it come out – Sect 6.

# 5. Modelling for Performance

How important is modelling for performance – given that we can't test every downhole condition in the lab?



Difference between an optimistic model and model based on stressed rock data similar to reservoir.

Example:

2-7/8in Premium Gun in 7in casing,  
No Gun Clearance.

12 in Mud filtrate invasion.

## 5. Modelling for Performance

Most current models rely on Sect 1 penetration and apply a correlation for rock strength, stress (in some models), casing, cement and gun clearance.

SPOT has 2 correlations and can use Sect 2/4 testing (as used in previous example), but still relies on converting the results back into Sect 1 penetration before predicting modelled penetration, good but not charge specific enough.

Schlumberger have a model and correlation based on a large number of stressed rock shots. With well documented and charge specific correlations.

This type of model is being considered by other contractors.

But all premium charges will need to be shot under various rock strength and stress conditions to make this work.



## 5. Modelling for Performance

Ref – EWAPS-12-18


Detailed review of hundreds of shots under stressed conditions into different rock types with different charges.

It is suggested that each charge can be characterised by a combination of factors which identify a relative slope/curve and height for penetration.

In addition each rock, pore pressure and confinement condition, can also be characterised by a single term – the Ballistic Indicator Function.

So going back to my earlier slide showing the performance of 3 similar charges :-

# 5. Modelling for Performance



## 6. Conclusions and Way Forward

Is penetration consistency in outcrop rock is an issue?

Are we shooting the target material in the right plane – perpendicular or parallel to bedding?

We are still getting significant variations in charge performance, is this due to target or charge consistency?

Should we continue to look at synthetic target development?

Should we look at a consistent way of modelling charge performance in stressed rock – if so what model?

Some possible ways forward –

## 6. Conclusions and Way Forward

Some possible ways forward –

Is penetration consistency in outcrop rock is an issue? **Even though Berea is now more consistent – we still have significant variation.**

Are we shooting the target material in the right plane – perpendicular or parallel to bedding? **Consistency is the main thing, shooting perpendicular to bedding does appear to create greater consistency.**

We are still getting significant variations in charge performance, is this due to target or charge consistency? **Some recent tests on commodity charges have shown some significant loading inconsistency.**

Should we continue to look at synthetic target development? **Ideally, a joint industry effort is worth the effort for price and consistency.**

Should we look at a consistent way of modelling charge performance in stressed rock – if so what model? **Ideally we need an industry agreed and tested model that can be used in all penetration models.**

**2013 APPS - KL**

**The Importance of Charge Testing in  
Delivering Well Performance**

**APPS-13-12**

**Thank You**

*Presented by*

Mark S Brinsden

Shell

Chair API SC19B



AMERICAN PETROLEUM INSTITUTE

Mark Brinsden  
API SC 19B